



## FNAH-602 醇酸磁漆

## FNAH-602 Alkyd Enamel

产品特性 Characteristics	干燥迅速、良好的光泽、耐候性、良好的施工性能。 Quick drying, good gloss, good weather resistance and good workability.		
产品用途 Uses	用于涂覆钢铁表面。 Used for steel surface. 诸如新建的钢梁初始涂装和运营中的钢梁重新涂装及维护涂装面漆。 As topcoat for initial painting of newly-built steel beam, or for re-painting or maintenance of the steel beam in use.		
颜色 Color	各色 All colors		
施工条件 Application method	无气喷涂 喷嘴尺寸 压力 稀释比率	Airless spray Nozzle tip Fluid pressure Thinning ratio	推荐 Recommended 0.4~0.5mm 100~150kg/cm <sup>2</sup> 0~5% 适用于无气喷涂、空气喷涂、刷涂及辊涂 May be applied by airless spray, air spray, brush, or roller.
稀释剂 Thinner	醇酸稀释剂 Alkyd thinner		
混合比率 Mixing ratio	单组分 One-pack		
涂装膜厚 Film thickness	干膜: 30μm/道 Dry film thickness:30μm /coat	湿膜: 52μm/道 Wet film thickness:52μm /coat	
固体含量 Solid content	58%		
比重 Specific gravity	1.2		
涂覆率 Coverage rate	理论值 : 0.09kg/m <sup>2</sup> /30μm Theoretical:0.09kg/m <sup>2</sup> /30μm	0.067L/m <sup>2</sup> /30μm 0.067 L/m <sup>2</sup> /30μm	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.
干燥时间 Drying time	温度 (°C) Temperature (°C)	10	20
	指触干燥 (hrs) Dry to touch (hrs)	1.5	1
	半硬干燥 (hrs) Dry hard (hrs)	12	7
			30



涂装间隔 Coating interval	Min. 最小 (hrs)	16	10	8
	Max. 最大 (hrs)	—	—	—
储存期限 Shelf life	一年 12 months			
包装规格 Packing specification	20kg/桶 20 kg/barrel			
表面处理 Surface preparation	配套底漆表面应清洁干燥，无污物。 The preceding primer surface must be clean, dry and free of contaminants. 注意施工与底漆的涂装间隔。 Pay attention to the coating interval to the primer.			
适用底材 Substrate:	裸钢或旧漆膜 Bare steel or old paint film.			
适用下涂 Primer coat:	醇酸底漆或参考我公司配套 Alkyd Primer, or refer to our coating system.			
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛，应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site.			
提醒注意 Declaration	本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。 The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.			