



TKCH-707 防锈油（船用）

TKCH - 707 Anticorrosive Oil (for ships)

产品特性 Characteristics	常温自干，具有较好的附着力和耐候性、耐水性、通用性。 Air-drying and general-purpose. Good adhesion with resistance to weather and water.	
产品用途 Uses	主要用于燃油舱的临时保护。 Mainly used for temporary protection of oil bunker.	
颜色 Color	棕红色 Brownish red	
施工条件 Application method	无气喷涂 Airless spray 喷嘴尺寸 Nozzle tip 压力 Nozzle pressure 稀释比率 Thinning ratio	推荐 recommended 0.5~0.6mm 100~150kg/cm ² 0~10%（重量比）(by weight)
	适用于无气喷涂、空气喷涂、刷涂及辊涂。 May be applied by airless spray, air spray, brush, or roller.	
稀释剂 Thinner	专用稀释剂 Special thinner	
混合比率 Mixing rate	单组分 One-pack	
涂装膜厚 Film thickness	干膜: 25μm/道 湿膜: 45μm/道 Dry film thickness :25μm/coat Wet: film thickness :45μm/coat	
固体含量 Solid content	40%	
比重 Specific gravity	0.9	
涂覆率 Spreading rate	理论值 : 0.06kg/m ² /25μm Theoretical: 0.06kg/m ² /25μm	L/m ² /25μm L/m ² /25μm
	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Practical: varies depending on the surface treatment, environment and application methods.	



熟化时间 Induction time 干燥时间 Drying time	表干≤5h Surface dry≤5h	实干≤24h Through dry≤24h			
涂装间隔 Coating interval	温度 (°C) Temperature Min. 最小 (hrs) Min. (hrs) Max. 最大 (days) Max. (days)	10 30	20 24	30 20	
储存期限 Shelf life	一年 12 months				
包装规格 Package	170kg/桶、18kg/桶 170 kg/barrel, 18 kg/barrel				
表面处理	用喷砂除锈方式除去铁锈和氧化皮达到 ISO Sa2.5 级或用电动工具处理表面达到 St3 级。 The rust and scale on the surface should be thoroughly cleaned by abrasive blasting to ISO Sa2.5, or treat the surface to ISO St3.0 by power tool cleaning.				
涂装配套 Coating system	底面合一 Self-priming				
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site.				
提醒注意 Declaration	本说明书所提供信息均为目前我方所掌握最全面正确的资料, 鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 此中所有信息均以我方确认为准。 The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.				